

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> A61L 15/06, C09J 133/06 C09J 133/10	<b>A1</b>	<b>(11) International Publication Number:</b> WO 91/14462 <b>(43) International Publication Date:</b> 3 October 1991 (03.10.91)
<b>(21) International Application Number:</b> PCT/GB91/00497 <b>(22) International Filing Date:</b> 28 March 1991 (28.03.91)  <b>(30) Priority data:</b> 9007100.2      29 March 1990 (29.03.90)      GB 9008629.2      17 April 1990 (17.04.90)      GB 9012567.5      6 June 1990 (06.06.90)      GB  <b>(71) Applicant (for all designated States except US):</b> SMITH & NEPHEW PLC [GB/GB]; 2 Temple Place, Victoria Embankment, London WC2R 3BP (GB).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only) :</b> PECK, Roger, Francis [GB/GB]; Roycot, 62 Silver Street, Stansted Mountfitchet, Essex CM24 8HD (GB).		<b>(74) Agent:</b> HOBBS, J., D.; Corporate Patents & Trade Marks Department, Smith & Nephew plc, Gilston Park, Harlow, Essex CM20 2RQ (GB).  <b>(81) Designated States:</b> AT (European patent), AU, BE (European patent), CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB, GB (European patent), GR (European patent), IT (European patent), JP, LU (European patent), NL (European patent), SE (European patent), US.  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> ADHESIVE COMPOSITIONS  <b>(57) Abstract</b> <p>A medical adhesive product is provided comprising a substrate, a pressure sensitive adhesive on one face of the substrate and a layer of a polymer composition on the surface of the pressure sensitive adhesive wherein the polymer composition has low or no significant tack at temperatures below that of skin temperature but which is a pressure sensitive adhesive at skin temperature. The product may be moisture vapour permeable and have a moisture vapour transmission rate of at least 500 gm m<sup>-2</sup> 24h<sup>-1</sup> at 37 °C and at a relative humidity difference of 100 to 10 %.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark				

ADHESIVE COMPOSITIONS

The present invention relates to medical adhesive products such as surgical dressings, surgical drapes, medical tapes and the like and in particular to such products having improved handling and performance characteristics.

Surgical drapes and other adhesive medical products comprising a polyurethane film coated on one surface with a layer of a pressure sensitive adhesive such as a polyvinylether or an acrylic adhesive. Examples of such products include those sold under the Trade Mark 'OpSite' by T.J. Smith and Nephew, Limited. Such products especially the larger size products tend to be difficult to handle because the adhesive tends to stick to itself during application. A product has now been found in which this problem has been alleviated in the form of (a) a substrate, (b) pressure sensitive adhesive on one face of the substrate and (c) a layer on the pressure sensitive adhesive of a composition which has low tack at below skin temperature but which is a pressure sensitive adhesive at skin temperature.

- 2 -

Accordingly the present invention provides a medical adhesive product comprising a substrate, a pressure sensitive adhesive on one face of the substrate and a layer of a polymer composition on the surface of the pressure sensitive adhesive wherein the polymer composition has low or no significant tack at temperatures below that of skin temperature but which is a pressure sensitive adhesive at skin temperature.

Skin temperature is normally in the range 28°C-35°C and the adhesive products of this invention will exhibit sufficient tack to adhere to the skin at skin temperatures whilst exhibiting no significant tack at ambient temperature (i.e. 25°C or less). For the purposes of this document "no significant tack" means that the adhesive in products of the invention will have little or no tendency to stick to themselves at ambient temperature. However when applied to the skin the tack will be sufficient to adhere to the skin within thirty seconds of being applied.

The substrate will suitably comprise a non-woven material, a fibrous material or filmic material. More suitably the substrate will comprise a filmic material with a relatively high moisture vapour permeability.

The substrate of the invention can be any of the

- 3 -

substrates used on conventional adhesive dressings. Such substrates include continuous flexible films.

The continuous films for use as a substrate in the invention can suitably have a thickness of 10 to 250 $\mu$ m more suitably have a thickness of 25 to 35 $\mu$ m, for example about 30 $\mu$ m.

Continuous flexible films for the substrate include both moisture vapour permeable and relatively moisture vapour impermeable films. Favoured are continuous moisture vapour permeable films and in particular those films which have a moisture vapour transmission rate of at least 500g/m<sup>2</sup>/24 hours at 37°C at 100% to 10% relative humidity difference (hereinafter g/m<sup>2</sup>/24 hrs<sup>-1</sup>) and preferably at least 1000g/m<sup>2</sup>/24 hrs<sup>-1</sup>, for example 1500-2000g/m<sup>2</sup>/24 hrs<sup>-1</sup>. Description 1 provides a method for determining Moisture Vapour Transmission Rate (MVTR).

Such moisture vapour permeable continuous films can advantageously render the adhesive product of the invention permeable to moisture vapour but impermeable to liquid and bacteria.

Apt moisture vapour permeable continuous films include polyester thermoplastic copolymers (for example

- 4 -

HYTREL manufactured by the Shell Chemical Company); polyetherpolyamides (for example PEBAX manufactured by ATO Chem) and polyurethanes (for example ESTANE manufactured by Goodrich Chemicals).

Favoured moisture vapour permeable continuous films comprise polyurethane. Suitable polyurethanes include hydrophilic water absorbing polyurethanes such as those disclosed in European Patent Application Nos 0107915 and 0147119, and British Patent No 1280631, linear polyether and linear polyester polyurethanes such as those known as Estane (available from Goodrich Chemicals) and blends of polyurethane with an incompatible polymer such as those disclosed in European Patent Application No 0046071.

An apt film for use in the invention is a 25 $\mu$ m thick film of a polyether-polyurethane known as Estane 4714F which film has moisture vapour transmission rate of approximately 1800g/m<sup>2</sup>/24 hours at 37°C at 100% to 10% relative humidity difference.

Favoured relatively moisture vapour impermeable continuous films for use in the invention include films of 1,2-polybutadiene such as those known as RB 810, RB 820 and RB 830 available from Japan Synthetic Rubber Company and films of styrene-butadiene block copolymers

- 5 -

including styrene-butadiene-styrene block copolymers such as those known as Kraton or Cariflex available from Shell Chemicals.

An apt continuous film of 1,2 polybutadiene for use in the invention is a 150 $\mu$ m thick film of RB 830.

An apt continuous film of styrene-butadiene-styrene copolymer is a 30 $\mu$ m thick film of Kraton 1101.

Suitable pressure sensitive adhesives include any of those normally employed in medical adhesive products. Examples of suitable pressure sensitive adhesives include vinyl ether and acrylic adhesives. More suitable the pressure sensitive adhesive should comprise an acrylic copolymer emulsion such as described in European Patent Application No 194881 which is herein incorporated by reference. Most suitably the pressure sensitive adhesive will comprise an acrylic ester copolymer as described in European Patent No 35399 which is herein incorporated by reference.

The pressure sensitive adhesive layer will suitably have a weight per unit area of 10-50 gm<sup>-2</sup>, more suitably have a weight per unit area of 20-35 gm<sup>2</sup>

- 6 -

and preferably a weight per unit area of 25-30 gm<sup>2</sup>.

The present invention provides polymers suitable for use as the polymer composition which comprise 60 - 96% of residues (X), 0 - 30% of residues (Y) and 0 - 10% of residues (Z) wherein (X) is an alkyl acrylate or methacrylate wherein the alkyl portions contains 12 - 20 carbon atoms, (Y) is an alkyl acrylate or methacrylate wherein the alkyl portion contains 1 to 11 carbon atoms, (Z) is a polar acrylate or methacrylate residue; and wherein the average number of carbon atoms present in (X) and (Y) is at least 12.

In another embodiment the invention provides polymers suitable for use as the polymer composition which polymers suitably comprise 50-96% of residues (X), 1-40% of residues (Y) and 1-10% of residues (Z) wherein (X), is an alkyl acrylate or methacrylate wherein the alkyl portion contains 12-20 carbon atoms (Y) is a hydrophilic acrylate or methacrylate ester and (Z) is a polar acrylate or methacrylate residue. Such adhesives form an important aspect of this invention.

The polar acrylate or methacrylate residues may be the acid or an amide thereof or the like. Most suitably Z is acrylic acid or methacrylate acid. Preferably Z is acrylic acid.



- 7 -

Generally the number of different monomers residues X and Y is not more than 4, more suitably not more than 3 and preferably not more than 2. This helps maintain sufficient regularity in the polymer for waxy properties (that is low tack) to be achieved at ambient temperature (eg. at 20°C).

The residues (X) are more aptly present in excess of 65%. Favourably the residues (X) are unbranched. It is desirable that the alkyl components in X contain 14 to 18 carbon atoms, for example cetyl, lauryl, stearyl or the like residues. The comments hereinbefore regarding component (A) may be consulted.

The residues (Y) are as hereinbefore referred to in consideration of residues (B).

Particularly apt polymers will contain 0 - 15% of residues (Y). Certain favoured polymer will contain 0 - 10% of residues (Y). Certain preferred polymers will contain 0% of residues (Y).

Thus certain preferred polymers of this invention will comprise 90 - 96% of residues (X) and 4 - 10% of residues (Z). In such composition residue Z is preferably the residue of acrylic acid. In such

- 8 -

compositions the residues (X) are aptly residues of 2 or 3 different monomers and are most aptly residues of 2 different monomers, for example a stearyl acrylate or methacrylate and a lauryl acrylate or methacrylate.

A particularly preferred polymer of this invention comprises the residues of stearyl methacrylate (47%), lauryl methacrylate (47%) and acrylic acid (6.0%).

The residues (X) are more aptly present in excess of 60%. It is desirable that the alkyl components in X contain 12 to 20 carbon atoms, for example cetyl, lauryl, stearyl or the like residues. The residues (X) can be suitably residues of an alkyl acrylate or methacrylate or combinations thereof which have a straight or branched chain. Favourably the residues (X) are straight. Suitably the alkyl group contains 16 to 20 carbon atoms. The residues (X) can favourably be residues of a straight chain alkyl group containing 16-18 carbon atoms such as cetyl methacrylate. The residues (X) preferably contain straight chain alkyl groups of 18 carbon atoms for example stearyl methacrylate.

The residues (Y) can be residues of a hydrophilic acrylate or methacrylate ester. The residues (Y) will

- 9 -

suitably be an alkyl acrylate or methacrylate substituted by one or more hydrophilic groups such as ether groups, amide group, hydroxyl groups, dialkyl amine groups and the like. Aptly the residues (Y) will contain one or more alkoxy groups, for example ether groups.

Aptly the residues (Y) will contain an alkoxy group containing 1-4 carbon atoms. Aptly the alkoxy group will be carried by an alkyl group of 1-6 carbon atoms. Apt alkoxy groups include methoxy, ethoxy, n-propoxy and n-butoxy groups. Apt alkyl groups substituted by such alkoxy groups include ethyl, n-propyl, n-butyl, isobutyl, sec-butyl and the like.

Other apt residues (Y) will contain a number of  $-(CH_2CH_2O)-$  residues, for example capped polyethylenoxide acrylates or methacrylates such as their monomethyl ethers such as the monomethyl ether of PEG 1000 acrylate.

Particularly apt adhesives will contain 1 - 40% of residues (Y). Certain favoured adhesives will contain 20 - 32% of residues (Y). Certain preferred adhesives will contain 26-30% of residues (Y), for example 28%.

- 10 -

Certain preferred adhesives employed in this invention will comprise 60-70% of residues (X) and 4 - 10% of residues (Z). In such compositions residue Z is preferably the residue of acrylic acid. In such compositions the residues (X) are aptly residues of 2 or 3 different monomers and are most aptly residues of 2 different monomers, for example a stearyl acrylate or methacrylate and a lauryl acrylate or methacrylate.

One favoured adhesive of the invention comprises Stearyl Methacrylate (66%) Butoxyethyl Acrylate (28%) Acrylic Acid (6%).

A further favoured adhesive of this invention comprises Stearyl Methacrylate (66%) Ethoxyethyl Methacrylate (28%) Acrylic Acid (6%).

A particularly preferred adhesive formulation employed in this invention comprises the residues of stearyl methacrylate (66%), 3 methoxybutylacrylate (28%) and acrylic acid (6%).

The relative proportions of residues (X), (Y) and (Z) will determine the temperature activated properties of the pressure sensitive adhesive.

The adhesive compositions of the invention can

- 11 -

optionally comprise in addition to the copolymer for example fillers or medicaments such as topically effective medicaments which includes chlorhexidine and its salts, cetrimide and silver sulphadiazine.

The polymer which comprises the coating of the pressure sensitive adhesive layer will suitably have a weight per unit area of  $1-20\text{gm}^{-2}$ , more suitably it will have a weight per unit area of  $3-10\text{gm}^{-2}$  and preferably a weight per unit area of  $4-8\text{gm}^{-2}$ , for example 5, 6 or  $7\text{gm}^{-2}$ . The thickness and continuity of the coating for the pressure sensitive adhesive layer should be sufficient to block the pressure sensitive adhesive layer at below skin temperature whilst simultaneously being of sufficient thickness to exhibit its pressure sensitive adhesive properties within a few second of being applied to the skin.

The polymer coating of the pressure sensitive adhesive layer should suitably have no significant tack at a temperature of less than  $20^{\circ}\text{C}$ , more suitably it should have no tack at a temperature of less than  $22^{\circ}\text{C}$  and preferably it should have no tack at a temperature of less than  $25^{\circ}\text{C}$ . More preferably it should have no significant tack at a temperature of less than  $28^{\circ}\text{C}$ . At temperatures above  $28^{\circ}\text{C}$  the polymer coating should preferably have sufficient tack thereby enabling the

- 12 -

coating the assume the properties of the pressure sensitive adhesive layer at skin temperture which is normally in the range of 28-35°C. The MVTR of the adhesive layer together with the polymer coating will aptly be at least  $500 \text{ gm}^{-2}$  and more aptly at least  $750 \text{ g m}^{-2}$  24hr at 37°C and at a realtive humidity. In practical terms the MVTR of the adhesive layer together with the polymer coating will be determined by its thickness and will rarely exceed  $2000 \text{ gm}^{-2}$ .

The MVTR of the completed product can be determined using the Payne Cup method as described in Description 1 at 37°C with a relative humidity difference of 100-10%. The MVTR of the completed product will favourably be at least  $350 \text{ gm}^{-2}$  24 hrs<sup>-1</sup>, more suitably at least  $500 \text{ gm}^{-2}$  and preferably at least  $650 \text{ gm}^{-2}$ .

In order to determine the MVTR of the backing layer by this method it is preferably to determine the MVTR of the substrate prior to adhesive coating. Alternatively the adhesive layer can be removed from the substrate of the completed device in any convenient manner for example by cryogenic separation or solvent dissolution.

The MVTR of the adhesive layer together with the

- 13 -

polymer coating is obtained mathematically by measuring the MVTR of the completed product and of the substrate alone and employing the formula  $d^{-1} = b^{-1} + a^{-1} + c^{-1}$  where d is the MVTR of the completed product, b is the MVTR of the substrate and a is the MVTR of the pressure sensitive adhesive layer, and c is the MVTR of the polymer coating.

From the previous disclosure it will be realised that in one embodiment the device of the invention provides for a medical adhesive product consisting essentially of the named layers. Such medical adhesive products include surgical drapes, surgical dressings, first-aid dressings, medical tapes for attachment of dressing or other items to the body, ostomy products and incontinence products.

For use as a surgical drape or surgical dressing the area of the device of the invention can be any suitable size for application to the body. For use as a surgical drape or surgical dressing such areas could be up to 84cm x 56cm, for example 45cm x 55cm, 45cm x 28cm, 20cm x 28cm, 15cm x 20cm, 15cm x 10cm, 10cm x 10cm or 5cm x 7cm.

A surgical drape or surgical dressing as previously described can be applied to the skin by any

- 14 -

suitable method. Particularly favoured forms of presentation are those described in European Patent Specification Nos. 161865 and 341045 which are herein incorporate by reference.

Surgical drapes and surgical dressing of the device of the invention can be applied without wrinkles, folds and channels being formed. The heat insulation provided by surgeons gloves allow the drapes or dressings coated with the waxy polymer to be handled easily allowing unhurried and methodical attachment by means of a gentle smoothing action. Contact with skin for a few second allows the polymer to melt and assume the properties of the pressure sensitive adhesive which adheres to the skin in the normal way. This property of the device of the invention offers particular advantages for large surgical drapes which are notoriously difficult to handle. It also offer economical advantages in that it reduces waste caused by application failure.

In a further embodiment the device of the invention can be a first-aid dressing of any suitable size or form for such dressings. For example as a strip as a fingertip dressing, as an anchor dressing or as an eye occlusion patch. Sizes of such products could be for example 3.8cm x 2.2cm, 7.5cm x 3.7cm or



- 15 -

7.5cm x 5cm in a further embodiment the device of the invention can be a medical tape in the form of a roll of varying width and length for example from 1.25cm x 10m to 30cm x 10m. In a further embodiment the device of the invention can be a product for ostomy care in the form of an adhesive face plate attached to which would be a gasket and the ostomy pouch. In a further embodiment the device of the invention can be a product for incontinence care in the form of an adhesive face plate to which the incontinence device could then be attached.

The resultant product can be provided on a bacteria proof pouch and sterilised by a convenient method such as gamma irradiation or ethylene oxide.

The invention will now be illustrated by reference to the following examples.

#### Example 1

A mixture of stearyl methacrylate (65.8g) 2-ethyhexyl acrylate (28.2g) and acrylic acid (6g) monomers and a solution of catalyst BCHPC (0.2g) in ethyl acetate (100g) was slowly added by means of dropper funnels to ethyl acetate (50g) heated under reflux (80°C) in a resin flask over a period of

- 16 -

approximately 6 hours. Further ethyl acetate (50g) was added to the mixture during the polymerisation to maintain the mixture in a viscous but ungelled state.

The resultant solution contained 33% by weight of the copolymer. The alkyl groups of the residues in the copolymer had an average of 13 carbon atoms.

The resulting adhesive coating was then applied at a weight per unit area of  $7 \text{ gm}^{-2}$  to a polyurethane film (30 gsm of Estane 1417) which had previously been coated on one surface with an acrylate ester copolymer pressure sensitive adhesive (PSA) at a weight per unit area of  $30 \text{ gm}^{-2}$ . The coating was applied to the layer of the film on which contained the coating of the acrylate ester copolymer PSA. The adhesive coating was pressure sensitive at  $28^{\circ}\text{C}$  which enabled dressings or drapes (10 x 10cm and 20 x 40cm) made from the coated film to be applied easily to the skin.

The MVTR of the completed product was found to be  $525 \text{ gm}^{-2} \text{ 24 hrs}^{-1}$ .

#### Examples 2 - 7

The following adhesives were prepared by the method of Example 1:

- 17 -

Example	2	3	4	5	6	7
Stearyl						
Methacrylate	47	66	84.6	80	75.5	66
Lauryl						
Acrylate	47	--	--	--	--	--
2 Ethylhexyl						
Acrylate	--	28	9.4	14	4.7	28
Acrylic Acid	6	6	6	6	--	--
Methyl						
Methacrylate	--	--	--	--	19.8	--
Acrylamide	--	--	--	--	--	6

The adhesive of Example 2 was particularly good exhibiting no significant tack at about 20°C but showing good pressure sensitive adhesive properties at 30°C.

Surgical drapes made as described in Example 1 employing the polymer of Example 2 were able to be applied without wrinkling, folds or channels being formed. The heat insulation provided by surgeons' gloves allow the drapes coated with the waxy polymer to be handled easily allowing unhurried and methodical attachment by means of a gentle smoothing action. Contact with the skin for a few seconds allowed melting of the polymer which then assumes pressure sensitive

- 18 -

adhesive properties which adhere to the skin in the normal way.

Examples 8 - 9

A mixture of stearyl methacrylate (65.8g) 3 methoxybutylacrylate (28.2g) and acrylic acid (6g) monomers and a solution of catalyst BCHPC (0.2g) in ethyl acetate (100g) was slowly added by means of dropper funnels to ethyl acetate (50g) heated under reflux (80°C) in a resin flask over a period of approximately 6 hours. Further ethyl acetate (50g) was added to the mixture during the polymerisation to maintain the mixture in a viscous but ungelled state.

The resultant solution contained 24% by weight of the copolymer.

The copolymer solution was applied at a weight per unit area of  $7 \text{ gm}^{-2}$  to a polyurethane film ( $30 \text{ gm}^{-2}$  of Estane 5714F) which had previously been coated on one surface with an acrylate ester copolymer pressure sensitive adhesive (PSA) at a weight per unit area of  $30 \text{ gm}^{-2}$ . The coating of the polymer was applied to the layer of the film which contained the coating of the acrylate ester copolymer PSA.

- 19 -

The adhesive coating was found to be non-tacky at 20°C but to be tacky and pressure sensitive at 28°C which enable dressings (10cm x 10cm) or drapes (20cm x 40cm) made from the coated film to be applied easily to the skin without wrinkling or folding.

The MVTR of the completed product was found to be  $677 \text{ gm}^{-2} \text{ 24 hrs}^{-1}$ .

The heat insulation provided by a surgeons gloves allowed the drapes coated with the waxy polymer to be handled easily allowing unhurried and methodical attachment by means of a gentle smoothing action. Contact with the skin for a few seconds allowed melting of the polymer which then assumes pressure sensitive adhesive properties which adhere to the skin in the normal way.

#### Example 9

Example 8 was repeated by the adhesive was prepared by substituting ethyl acetate for acetone in the same proportions. The reflux temperature was 60°C and was carried out for approximately 12 hours.

- 20 -

Description 1The Payne Cup Method of MVTR Determination

Discs of the material under test are clamped over Payne Permeability Cups (flanged metal cups) using sealing rings and screw clamps. The flanges on the cups are previously coated with an acrylic adhesive to a weight per unit area of  $30 \text{ gm}^{-2}$ . The exposed surface area of the test sample is  $10 \text{ cm}^2$ . Each cup contains approximately 10 ml of distilled water.

After weighing the cups are placed in a fan assisted oven which is maintained at  $37 \pm 1^\circ\text{C}$ . The relative humidity within the oven is maintained at approximately 10% by placing 1kg of anhydrous 3-8 mesh calcium chloride on the floor of the oven.

The cups are removed after 24 hours, allowed to cool for 20 minutes and re-weight. The MVP of the test material is calculated from the weight loss and expressed in units of grams of weight per square metre per 24 hours.

- 21 -

CLAIMS

1. A medical adhesive product comprising a substrate, a pressure sensitive adhesive on one face of the substrate and a layer of a polymer composition on the surface of the pressure sensitive adhesive wherein the polymer composition has low or no significant tack at temperatures below that of skin temperature but which is a pressure sensitive adhesive at skin temperature.
2. A product as claimed in claim 1 which is moisture vapour permeable and has a moisture vapour transmission rate of at least  $500\text{gm m}^{-2} \text{ 24hr}^{-1}$  at  $37^{\circ}\text{C}$  and at a relative humidity difference of 100 to 10%.
3. A product as claimed in claim 1 or claim 2 wherein the substrate is a continuous polymeric film, an apertured polymeric film, a knitted fabric, or a woven or non-woven fibrous fabric.
4. A product as claimed in any one of claims 1 to 3 wherein the pressure sensitive adhesive layer is a continuous or discontinuous layer.
5. A product as claimed in any one of claims 1 to 4 wherein the polymer composition has a moisture vapour transmission rate, as a continuous layer, of at least

- 22 -

450gm m<sup>-2</sup> 24hr<sup>-1</sup> at 37°C and at a relative humidity difference of from 100 to 10%.

6. A product as claimed in any one of claims 1 to 5 in which the pressure sensitive adhesive is a vinyl ethyl based adhesive or an acrylic based adhesive.
7. A product as claimed in any one of claims 1 to 6 in which the polymer composition comprises an acrylic polymer containing residues of an alkyl acrylate or methacrylate in which the alkyl portion contains from 12 to 20 carbon atoms.
8. A product as claimed in any one of claims 1 to 7 in which the polymer composition comprises 60-96% of residues (X), 0-30% of residues (Y) and 0-10% of residues (Z) wherein (X) is an alkyl acrylate or methacrylate wherein the alkyl portion contains 12-20 carbon atoms, (Y) is an alkyl acrylate or methacrylate wherein the alkyl portion contains 1 to 11 carbon atoms, (Z) is a polar acrylate or methacrylate residue and wherein the average number of carbon atoms present in (X) and (Y) is at least 12.
9. A product as claimed in any one of claims 1 to 8 in which the polymer composition comprises 50-96% of residues (X), 1-40% of residues (Y) and 1-10% of



- 23 -

residues (Z) wherein (X) is an alkyl acrylate or methacrylate wherein the alkyl portion contains 12 to 20 carbon atoms, (Y) is a hydrophilic acrylate or methacrylate ester and Z is a polar acrylate or methacrylate residue.

10. A product as claimed in any one of claims 1 to 9 in which the polymer composition comprises about 47% of residues of stearyl methacrylate, about 47% of residues of lauryl methacrylate and about 6% acrylic acid residues.

11. A product as claimed in any one of claims 1 to 9 in which the polymer composition comprises about 66% stearyl methacrylate residues, about 28% 3-methoxybutylacrylate residues and about 6% acrylic acid residues.

12. A product as claimed in any one of claims 1 to 11 in which the polymer composition has no significant tack at temperatures of less than 28°C.

13. A product as claimed in any one of claims 1 to 12 in which the polymer composition also comprises a filler.

14. A product as claimed in any one of claims 1 to 13

- 24 -

in which the polymer composition also comprises a topically effective medicament.

15. A product as claimed in any one of claims 1 to 14 in the form of a wound dressing, a surgical incise drape, or an applicator for an ostomy device.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 91/00497

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC <sup>5</sup> :    A 61 L 15/06, C 09 J 133/06, C 09 J 133/10		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
IPC <sup>5</sup>	A 61 L, C 09 J	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup>		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b>		
Category <sup>9</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
X	EP, A, 0062682 (NICHIBAN) 20 October 1982 see claims; examples <div style="text-align: center;">---</div>	1-11,13-15
X	US, A, 4608249 (S. OTSUKA) 26 August 1986 see column 1, lines 60-68; column 2, lines 46-58 and 18-31; column 3, lines 11-17; column 4, lines 50-64; claims <div style="text-align: center;">---</div>	1-11,13-15
A	US, A, 3763858 (G. BUESE) 9 October 1973 see column 2, lines 15-24 <div style="text-align: center;">---</div>	12
A	EP, A, 0285550 (SEKISUI) 5 October 1988 see claims; examples <div style="text-align: center;">---</div> <div style="text-align: right;">./.</div>	1-15
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><sup>10</sup> Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p> </div> </div>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
21st June 1991		01.08.91
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		Mme Dagmar FRANK

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, " with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP, A, 0035399 (SMITH AND NEPHEW) 9 September 1981 cited in the application  ---	
A	US, A, 4880683 (R. STOW) 14 November 1989 cited in the application  -----	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.**

GB 9100497

SA 46169

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 23/07/91  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A- 0062682	20-10-82	JP-A- 57077617	15-05-82
		AU-A- 7722981	11-05-82
		WO-A- 8201317	29-04-82
		US-A- 4505891	19-03-85
-----			
US-A- 4608249	26-08-86	None	
-----			
US-A- 3763858	09-10-73	None	
-----			
EP-A- 0285550	05-10-88	JP-A- 63246325	13-10-88
		US-A- 4971799	20-11-90
-----			
EP-A- 0035399	09-09-81	AU-B- 544431	30-05-85
		AU-A- 6804681	10-09-81
		CA-A- 1167598	15-05-84
		GB-A, B 2070631	09-09-81
		JP-A- 56133308	19-10-81
		US-A- 4379881	12-04-83
-----			
US-A- 4880683	14-11-89	AU-B- 556463	06-11-86
		AU-A- 9191182	07-07-83
		CA-A- 1217985	17-02-87
		EP-A, B 0083499	13-07-83
		JP-A- 58154778	14-09-83
-----			

